



## K-80-203

**K-80-203** is a solvent-free emulsion of diglycidyl ether of bisphenol A having an average EEW of about 190. K-80-203 is suggested for use as a fiberglass size in applications such as the reinforcement of epoxy resin structures.



### PHYSICAL PROPERTIES

**Stabilizer:** Nonionic

**Viscosity (cps):** 200 – 5,000 (RV3/10/73 - 77 F)

**Percent Solids (%):** 55.0 – 57.0

**pH:** 6.0 - 8.2

**Weight per Gallon:** 8.99 lbs

**Particle Size:** 100 - 1000 nm (Volume %)

**Freeze/Thaw Stable:** No

### ADDITIONAL INFORMATION

Mix well before using.

### STORAGE AND HANDLING

**Shelf Life:** Six months at 70° F. Store in closed containers.

#### IMPORTANT NOTICE TO CUSTOMER:

The recommendations and data contained in this Product Data Sheet for use of this product are based on information Franklin believes to be reliable. They are offered in good faith without guarantee, as conditions and methods of use of our product by Customer are beyond Franklin's control. Customer must determine the suitability of the product for a particular application before adopting it on a commercial scale.

All orders for Franklin products shall be subject to Franklin International, Inc.'s Standard Terms and Conditions of Sale which may be found [http://www.franklin.com/Terms\\_and\\_Conditions.aspx](http://www.franklin.com/Terms_and_Conditions.aspx) ("Standard Terms"). Different or additional terms proposed by Customer are expressly rejected and shall not become part of the agreement between Customer and Franklin International, Inc. with respect to any order. Contact Franklin International, Inc. immediately if you cannot access our Standard Terms and we will provide you a copy upon request. Any sale of products by Franklin to Customer is expressly conditional upon Customer's consent to the Standard Terms, and Customer's acceptance of any performance by, or receipt of products from, Franklin International, Inc. shall constitute Customer's acceptance of the Standard Terms and Conditions of Sale.

© Copyright 2014. All rights reserved. Franklin International. Revised 02/25/14.